	CAMBODIAN CHEMICAL SUPPLY CO., LTD.		Doc. No: TDS-PRD-004
	Name	HOMY- EXT	Revised No : 01
	Type	Technical Data Sheet	Page No : 1 of 4

HOMY-EXT is a pure acrylic-base Flat paint. It is specially formulated for all weathers conditions. This standard grade paint is good adhesion on exterior (façade) and interior walls.

ADVANTAGES	<ul style="list-style-type: none"> • Easy use • Matt and Smooth Feel • Low Ordour • Cost saving 	
USE	On	Prime or non-prime Plastered Surface, Rendered Surface, Cement board and Gypsum board.
	For	Decoration and protection of the above substrates.
COMPOSITION	Pigments	- Fine particle calcium carbonate - Non-Lead Chromate Colorant
	Binder	Type : Green Acrylic 100% Reference : Allnex, Arkema, Optichem Archroma
	Thinner	Clean Water
	Special Additive	Surfactant : APEO free Preservative : Formaldehyde free, Mercury free pH Stabilizer : Ammoniac free Reference : DOW Chemical, Elementis, Lonza, Lorama, Troy
PRODUCT PROPERTIES	Solid %	- By Weight : 59 ± 1 - By Volume: 42 ± 1
	Color	- Multi Choices - Reference: BASF, CLARIANT, LORAMA
	Texture	Matt and smooth finish
	Specific Gravity	1.46 ± 0.02 g/ml
	Drying Time @ 30 °C	Touch Dry: 20-30 minutes Hard Dry : 48 hours
	Recommended Wet Film Thickness Per Coat	520 - 640µ Reference: Scrub Test @ 1,000 cycles



CAMBODIAN CHEMICAL SUPPLY CO., LTD.

Doc. No: TDS-PRD-004

Name

HOMY- EXT

Revised No : 01


Type

Technical Data Sheet

Page No : 2 of 4

	Recommended Dry Film Thickness Per Coat	220 - 270μ Reference: Scrub Test @ 1,000 cycles
	Recoating Interval	2 hours @ 30 °C
	Practical Coverage	55 m ² /pail/2coats
	Pack Size	26 kgs
INSTRUCTION FOR USES	Surface Preparation	Ensure that the surfaces are free from loose particles, dirt, dust, grease, oil, wax. Make good for any surface defected, clean thoroughly and dry.
	Application Methods	By using Roller / Soft-Brush Thin with some 10% of clean water and apply by using Roller and/or Soft-Brush. By Using Air Spray Dilute the paint with 20% of clean water.
	Previously Painted Surface	Remove all unstable paint film, loose chalk, dust and other foreign matters. Treat surface with Cam-Paint Penetrate Primer "PROTAN" to strengthen substrate condition.

Sequence	Complement Product		No of Coat	For Loose Substrate
	Exterior	Interior		
Plaster	VIMEAN SOR/BAN.ce	VIMEAN SOR/ BAN.ce	2 or 3	
Primer	PREVALENT	PREVALENT	1	PROTAN
Finish Coat	HOMY EXT		2 or 3	

	CAMBODIAN CHEMICAL SUPPLY CO., LTD.		Doc. No: TDS-PRD-004
	Name	HOMY- EXT	Revised No : 01
	Type	Technical Data Sheet	Page No : 3 of 4

NOTE:

The above information is given to the best of our knowledge based on testing and practical application.

However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself. We reserve the right to alter the given data without prior notice.

*Contact for further information:
 Mr. Vey Bora, Production Manager
 H/P: (+855) 15 888 003 / 78 885 443
 E-mail: veybora@campaint-ccsc.com.kh*