
	CAMBODIAN CHEMICAL SUPPLY CO., LTD.		Doc. No : TDS-PRD-011
	Name	M-33	Revised No : 0
	Type	Technical Data Sheet	Page No : 1 of 3

M-33 is a Medium Gloss Architectural Alkyd paint with special additives. Designed for Iron Black Steel and Wooden for decorative It has good quality for exterior and Interior.

ADVANTAGES	<ul style="list-style-type: none"> ➤ Quick drying time and easy to use ➤ Good Color Retention ➤ Surface Hard ➤ Good adhesion and Durability 	
USE	<i>On</i>	Black and Galvanized steel Surface, and Soft and hard Wood.
	<i>For</i>	Decoration and protection of the above Surface and Durability.
COMPOSITION	<i>Pigments</i>	- Fine particle Titanium dioxide, Calcium Carbonate (CaCo3) - Non-Lead Chromate Colorant
	<i>Binder</i>	Type : Alkyd Resin Reference : Haiphong
	<i>Thinner</i>	Cam-Paint thinner DW-5050
	<i>Special Additive</i>	Drier : Lead(Pb) free Preservative : Mercury free Reference : TROY
PRODUCT PROPERTIES	<i>Solid %</i>	- By Volume: 63
	<i>Color</i>	- Multi Choices - Reference: CLARIANT, POPCO, PANEX Pigment
	<i>Texture</i>	Medium Gloss (GU44@60)
	<i>Specific Gravity</i>	1.23 ±03 g/ml
	<i>Drying Time @ room temperature</i>	Touch dry: 2H
	<i>Recommended Wet Film Thickness Per Coat</i>	45 –60µm
	<i>Recommended Dry Film Thickness Per Coat</i>	35-50 µm

 CAM-PAINT គ្រីណិស៊ីប៉ាតិ	CAMBODIAN CHEMICAL SUPPLY CO., LTD.		Doc. No : TDS-PRD-011
	Name	M-33	Revised No : 0
	Type	Technical Data Sheet	Page No : 2 of 3

	<i>Recoating Interval</i>	6-8hours @ 30°C
	<i>Practical Coverage</i>	6m ² /kg/coat Smooth Surface
	<i>Pack Size</i>	1 kg/metal pail; (3.8 kgx4)(1×12)cotton box
INSTRUCTION FOR USES	<i>Surface Preparation</i>	Ensure that the surfaces are free from loose particles, dirt, dust, grease, oil, wax. Make good for any surface defected, clean thoroughly and dry.
	<i>Application Methods</i>	<p>By using Roller / Soft-Brush Thin with 10% of DW-5050 thinner and apply by using Roller and/or Soft-Brush.</p> <p>By Using Air Spray Dilute the paint with 20% of DW-5050 thinner</p>
	<i>Previously Painted Surface</i>	Remove all unstable paint film, loose chalk, dust and other foreign matters.

Sequence	Complement Product			No of Coat	Remark
	<i>Black steel</i>	<i>Wood</i>	<i>Concrete</i>		
Primer	Red& Gray primer	Special primer	N/A	1	1 Coat of primer and 1-2 Coat of Top Coat

NOTE:

The above information is given to the best of our knowledge based on testing and practical application. However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself. We reserve the right to alter the given data without prior notice.

Contact for further information:
 Mr. Vey Bora, Production Manager
 H/P: (+855) 15 888 003 / 78 885 443
 E-mail: veybora@campaint-ccsc.com.kh