
	CAMBODIAN CHEMICAL SUPPLY CO., LTD.		Doc No: TDS-PRD-001
	Doc Name	VITAL Technical Data Sheet	Revised No: 01
	Doc Type	TDS	Page: 2 of 3

	Recommended Wet Film Thickness Per Coat	75 - 100μ
	Recommended Dry Film Thickness Per Coat	25 - 35μ Reference: - Scrub Test @ 5,000 cycles at least - Hiding Power over 75%
	Recoating Interval	2 hours @ 30 °C
	Practical Coverage	≈ 16 m ² /liter/coat
	Pack Size	15 Liters
INSTRUCTION FOR USES	Surface Preparation	Ensure that the surfaces are free from loose particles, dirt, dust, grease, oil, wax. Make good for any surface defected, clean thoroughly and dry.
	Application Methods	By using Roller / Soft-Brush Thin with some 10% of clean water and apply by using Roller and/or Soft-Brush. By Using Air Spray Dilute the paint with 20% of clean water.
	Previously Painted Surface	Remove all unstable paint film, loose chalk, dust and other foreign matters. Treat surface with Cam-Paint Penetrate Primer PROTAN™ to strengthen substrate condition.

Sequence	Complement Product		No of Coat	For Loose Substrate
	<i>Exterior</i>	<i>Interior</i>		
Plaster	VIMEAN SOR	VIMEAN SOR	2 or 3	
Primer	MAX EXTRA E	MAX EXTRA E	1	PROTAN
Finish Coat	VITAL		2 or 3	

	CAMBODIAN CHEMICAL SUPPLY CO., LTD.		Doc No: TDS-PRD-001
	Doc Name	VITAL Technical Data Sheet	Revised No: 01
	Doc Type	TDS	Page: 3 of 3

NOTE:

The above information is given to the best of our knowledge based on testing and practical application.

However, since we cannot anticipate or control the many conditions under which our products may be used, we can only guarantee the quality of the product itself. We reserve the right to alter the given data without prior notice.

Key Contact Person:

Mr. Vey Bora, Production Manager
H/P: (+855) 15 888 003 / 78 885 443
E-mail: veybora@campaint-ccsc.com.kh